



TECHNICAL DATA SHEET FOR MAX-02 75% VIRGIN PTFE, 25% Glass

PHYSICAL PROPERTIES

Low Flow Polytetrafluoroethylene (nff)

Test Method	Properties	Units	Typical Value
ASTM 4745-14	Tensile	PSI	2270 min
ASTM 4745-14	Elongation	%	240 min
ASTM D2240	Shore Hardness	Shore D	60 min
ASTM D792-08	Specific Gravity	G/CC	2.180-2.250

Fiber glass is by far the most used filler for PTFE. Glass fiber is typically blended with PTFE at 5%-40% depending on customer specs. Blending glass with PTFE gives it the ability to lower creep, boost wear resistance, and give the material an overall higher compressive strength.

The above information is, to the best of our knowledge, true and accurate. No warranty, expressed or implied, is made or intended. The use of this product should be determined by the user, based on their appraisal.

Contact:

PTFE Industries

9426 Katy Freeway BLDG 7

Houston, TX 77055