



## TECHNICAL DATA SHEET FOR MAX-13 75% VIRGIN PTFE, 25% Carbon Fiber

### PHYSICAL PROPERTIES

Low Flow Polytetrafluoroethylene (nff)

Test Method	Properties	Units	Typical Value
ASTM 4745-14	Tensile	PSI	3250 min
ASTM 4745-14	Elongation	%	200 min
In House	Shore Hardness	D	55-65
ASTM D792-08	Specific Gravity	G/CC	2.150-2.250

The above information is, to the best of our knowledge, true and accurate. No warranty, expressed or implied, is made or intended. The use of this product should be determined by the user, based on their appraisal.

Contact:  
PTFE Industries  
9426 Katy Freeway BLDG 7  
Houston, TX 77055